

Alleima® 13C26 medical strip

Strip steel

Datasheet

Alleima® 13C26 is a martensitic stainless chromium steel supplied in strip form. The grade is mainly supplied in annealed or cold rolled condition, characterized by:

- Soft delivery condition
- Good formability
- Good blanking properties

After heat treatment, Alleima® 13C26 is characterized by:

- High hardness
- Good corrosion resistance
- High wear resistance

Standards

- DIN: X65Cr13

Product standards
ISO 7153-1

Chemical composition (nominal)

Chemical composition (nominal) %

C	Si	Mn	P	S	Cr
0.68	0.4	0.7	≤0.025	≤0.010	13

Applications

Alleima® 13C26 is mainly used for ophthalmologic and surgical blades. It is also a standard grade for razor blades and used for different types of knives.

Forms of supply

The strip can be supplied either in coils or as straightened lengths of 0.5 - 4.0 meter (1.6 - 13.1 feet). The coil weight is max 5 kg/mm (280 lb/in.) of strip width.

Hardening and tempering of the strip steel is required to achieve the correct finish and to meet the properties necessary for the end user.

Dimensions

Thickness		Width	
mm (in.)		mm (in.)	
min.	max.	min.	max.
0.1 (0.0039)	1.0 (0.039)	5 (0.197)	350 (13.78)


Other sizes can be supplied to meet specific requirements.

Tolerances

The thickness and width tolerances are +/- tolerances to the nominal size. The normal tolerance classes for most of our strip products are T2 and B1. Tighter tolerances as well as other tolerance limits can be offered upon request.

Heat treatment

Hardening data and Tempering data: Piece hardening



A = Austenitizing, Q = Quench, T= Tempering

Austenitizing

Belt furnace. Time in furnace according to table

Thickness	Thickness	Time
mm	in.	minutes

2.5	0.100	5
3.0	0.118	6
3.25	0.128	7
3.5	0.138	8
3.45	0.148	10
4	0.157	12


Quench

As rapid as possible, for optimal result 600°C (1110°F) should be reached within 2 minutes or less.

Tempering 2 hours

Hardness	Temperature
HRC	°C (°F)
59	175 (345)
57	225 (435)
55	350 (660)

Hardening data and Tempering data : Batch hardening



A = Austenitizing, Q = Quench, T = Tempering

Temperature should be equalized at 850°C (1560°F) for 30 minutes to avoid unnecessary temperature variations.

Austenitizing

Batch furnace. 30 minutes in furnace.

Quench


As rapid as possible, for optimal result 600°C (1110°F) should be reached within 2 minutes or less.

Tempering 2 hours

Hardness	Temperature
HRC	°C (°F)
59	175 (345)
57	225 (435)

Hardness versus tempering temperature

Hardness, HRC



Brittleness occurs with tempering above 450°C (840°F).

Mechanical properties

As delivered	Tensile strength Rm	Hardness	
	MPa (ksi)	HV	HRC
Annealed	max. 800(116)	max. 250	max. 22
Cold rolled	830-1050 (121-152)	260-328	24-33
Hardened and tempered	1700-2000 (247-290)	545-633	52-57

Mechanical properties can vary depending on the tempering parameters

Physical properties

The physical properties of a steel are related to a number of factors, including alloying elements, heat treatment and manufacturing route, but the data presented below can generally be used for rough calculations.

Density : 7.7 g/cm³ (0.28 lb/in.³)

免责声明：山特维克不提供任何意图或可能被视为从医疗/生物学/安全角度以任何方式推荐或建议任何医疗材料、仪器和/或医疗器械的设计、适用性、适当性或效果的产品或服务。

